

# TECHNICAL SPECIFICATION

## 1. GENERAL

### 1.1 Scope

Cable type	Application
Antcore™ Extreme Micro Cable (180µm fiber)	Air blowing installation cable

### 1.2 Reference

The following international specifications were used as reference documents for the cables provided by Navigator:

IEC 60793-1	Optical fiber Part 1: Generic specifications
IEC 60793-2	Optical fiber Part 2: Product specifications
IEC 60794-1	Optical fiber cable Part 1-2: Generic specification-basic optical cable test procedures
IEC 60794-5	Optical fiber cables- Part 5: sectional specification -Micro duct cabling for installation by blowing
ITU-T G.650	Definition and test methods for the relevant parameters of single-mode fibers
ITU-T G.652	Characteristics of a single-mode optical fiber and cable
ITU-T G.657	Characteristics of a single-mode optical fiber and cable
EIA/TIA 598	Color code of fiber optic cables
ANSI/ICEA S-87-640 and Telcordia® GR-20-CORE	

### 1.3 QR Guard™

QR Guard™ is a multifunctional online platform that revolutionizes how distributors and network operators keep tabs on the status of Navigator fiber cables, ensuring efficient operations, accurate record-keeping, and valuable insights for future product development. Providing unique features including:

- Distributor exclusive management interface
- Installation record archiving
- Written guidelines and visual demonstrations

QR Guard™ plays a vital role in mitigating the costly consequences of mishandling while enabling efficient network expansion in response to evolving market demands. Scan the QR code in the bottom left corner to find our more.



## 2. OPTICAL FIBER


ITU-T G.657.A2		
Category	Description	Specifications
Optical Specifications	Attenuation @1310 nm (Max.)	0.34dB/km
	Attenuation @1550 nm (Typical/ Max.)	≤0.20/0.22 dB/km
	Dispersion coefficient	@1288~1339nm ≤3.5ps/nm·km @1271~1360nm ≤5.3ps/nm·km @1550nm ≤18ps/nm·km @1625nm ≤22ps/nm·km
	Zero Dispersion Wavelength	1300~1324 nm
	Zero Dispersion Slope	≤ 0.092 ps/nm <sup>2</sup> ·km
	PMD Link value (M=20cables Q=0.01%) maximum PMDQ	0.20 ps/√km
	Cable Cutoff Wavelength (λ <sub>cc</sub> )	≤1260 nm
	Macro bending Loss (10 turns; Φ30 mm) @1550 nm (10 turns; Φ30 mm) @1625 nm (1 turns; Φ20 mm) @1550 nm (1 turns; Φ20 mm) @1625 nm (1 turns; Φ15 mm) @1550 nm (1 turns; Φ15 mm) @1625 nm	≤ 0.03 dB ≤ 0.1 dB ≤ 0.1 dB ≤ 0.2 dB ≤ 0.5 dB ≤ 1.0 dB
	Mode Field Diameter @1310 nm	(8.6-9.2) ±0.4μm
	Dimensional Specifications	Cladding Diameter
Cladding non circularity		≤1.0%
Coating diameter		180±10μm
Coating non circularity		≤6%
Cladding / coating concentricity error		≤6μm
Core/clad concentricity error		≤0.5μm
Cladding Non-Circularity		≤1.0%
Mechanical Specifications	Proof stress	≥0.69Gpa



### 3. CABLE STRUCTURE

#### 3.1 Cable type

Antcore™ Extreme Micro Cable



#### Features & Application

- Small diameter
- Semi-dry water blocking
- Perfect cable structure
- Easy for blowing
- Saving the source of duct

#### Technical Specifications

Dimensional properties	Fiber type	180um G657A2							
	Fiber count	72	96	144	192	288	432	576	864
No. of fibers per tube	12	12	24	24	24	24	24	36	
Stranding no.-tube No./filler No.	6/0	8/0	6/0	8/0	12/0	18/0	24/0	24/0	
Cable OD-mm(in )	4.2(0.17)	4.7(0.19)	5.1(0.20)	5.8(0.23)	7.6(0.30)	8.2(0.32)	8.8(0.35)	10.0(0.39)	
Cable weight- kg/km(lb/1000ft)	17(11.4)	23(15.5)	26(17.5)	36(24.2)	60(40.3)	58(39.0)	83(55.8)	106(71.2)	
Environmental Specifications	Operation temperature range	-40°C to + 70 °C (-40 ° F to 158 ° F)							
	Installation temperature range	-30 °C to + 60 °C (-22 ° F to 140 ° F)							
	Transport and storage temperature range	-40 °C to + 70 °C (-40 ° F to 158 ° F)							
Mechanical Specifications	Max tensile load (MAT)	1*w							
	Crush resistance-N/10cm(lb/in)	500(28.6)							
	Minimal installation bending radius	20*D							
	Minimal operation bending radius	10*D							

\*Note: D =cable diameter, W=cable weight/km;



## 4. TEST REQUIREMENTS

### Fiber test standard

Mode field diameter	IEC 60793-1-45
Mode field Core/clad concentricity	IEC 60793-1-20
Cladding diameter	IEC 60793-1-20
Cladding non-circularity	IEC 60793-1-20
Attenuation coefficient	IEC 60793-1-40
Chromatic dispersion	IEC 60793-1-42
Cable cut-off wavelength	IEC 60793-1-44

### Performance testing list

#### 4.1 Tensile strength test

Reference standards	IEC 60794-1-21 E1
Sample length	No less than 50 meters
Load	MAT
Duration time	1 minute
Test results	Additional attenuation $\leq 0.10\text{dB}$
	No damage to outer jacket and inner elements

#### 4.2 Compressive strength test

Reference standards	IEC 60794-1-21 E3
Load	Crush resistance
Duration time	1minute
Test number	3
Test results	Additional attenuation $\leq 0.10\text{dB}$
	No damage to outer jacket and inner elements

#### 4.3 Impact resistance test

Reference standards	IEC 60794-1-21 E4
Impact energy	1J
Radius	12.5mm
Impact points	5
Impact number	1



Test result	Additional attenuation $\leq 0.10\text{dB}$
	No damage to outer jacket and inner elements

#### 4.4 Cyclic flexing test

Reference standards	IEC 60794-1-21 E6
Bending radius	20*D
Cycles	25 cycles
Load	150N
Test result	Additional attenuation $\leq 0.10$
	No damage to cable elements

#### 4.5 Bend test

Reference standards	IEC 60794-1-21 E11
Mandrel diameter	20*D
Turn number	3
Cycles	4
Test result	Additional attenuation $\leq 0.10\text{dB}$
	No damage to outer jacket and inner elements

#### 4.6 Twist test

Reference standards	IEC 60794-1-21 E7
Sample length	2m
Angles	$\pm 180$ degree
Load	150N
Cycles	10
Test result	Additional attenuation $\leq 0.10\text{dB}$
	No damage to cable elements

#### 4.7 Abrasion test

Reference standards	IEC 60794-1-21 E2B
Experiment method	The wool felt should be thoroughly impregnated with water
Frequency	50cycles/min
Load	20N
Cycles	10
Test result	The marking should be legible after test

#### 4.8 Water penetration test



Reference standards	IEC 60794-1-22 F5
Height of water column	1m
Sample length	3m
Test time	24 hours
Test result	No water seepage from the opposite end of the sample

#### 4.9 Temperature cycling test

Reference standards	IEC 60794-1-22 F1
Temperature step	+20 °C → -40 °C → +70 °C → +20 °C
Time per each step	≥ 8 hours
Cycles	2
Test result	Attenuation variation for reference value (the attenuation to be measured before test at +20±3 °C) ≤ 0.15dB/km

#### 4.10 Environmental performance

Test Standard	RoHS
Test result	Pass the test.

Remark: The test wavelength is 1550 nm.

### 5. COLOR CODE SCHEME

Fiber color	blue	orange	green	brown	slate	white	red	black	yellow	violet	pink	aqua
Tube color	blue	orange	green	brown	slate	white	red	black	yellow	violet	pink	aqua

Note: color rings will be used on 13th-36th fibers;  
color rings will be used on 13th-24th loose tubes;

### 6. SHEATH MARKING

